INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Royal Vriesco B.V. - A House of Happiness
Meester P.J. Troelstraweg 147-2
8919 AA LEEUWARDEN - FRIESLAND
Netherlands

Your notice of	Your reference	Date
04-04-2024		30-04-2024

Analysis Report 24.01860.02

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2407113	Supreme F.R.	04-04-2024

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Samples

T2407113
Supreme F.R.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: T2407113 - Supreme F.R.

Washing and drying

Date of ending the test	11-04-2024
Standard used	ISO 6330 (2021)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	6N- 60°C (2021)
Drying method	A = Line dry (2021)
Number of washing cycles	20
Mass of the test specimens	790 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2407113_01d

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: **T2407113_01d - Supreme F.R.**

Classification of materials according to their reaction to fire - "Electric burner"

Date of ending the test	16-04-2024
Standard used	NF P92-503 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	-
Dimension of the specimens	600 mm x 180 mm x 1 mm
Weight (g/m²)	286
Conditioning	23°C, relative humidity 50% Minimum 7 days or until constant mass is achieved

	Length		Width	
	Front	Back	Front	Back
Hole formation	yes	yes	yes	yes
Max. afterflame time (s)	0	0	0	0
Afterglow	no	no	no	no
Afterglow with propagation in area > 25 cm	no	no	no	no
Damaged length (cm)	20.5	23.0	22.5	20.0
Damaged width (cm) in area >45 cm	0	0	0	0
Flaming molten droplets	no	no	no	no
Non-flaming molten droplets	yes	yes	yes	yes
Flaming debris	no	no	no	no
Non-flaming debris	no	no	no	no
Average damaged length (cm)	21.5			
Average damaged width (cm) in area > 45 cm	0			

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: **T2407113_01d - Supreme F.R.**

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test	19-04-2024
Standard used	NF P92-504 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	-
Dimension of the specimens	460 mm x 230 mm x 1 mm
Weight (g/m²)	286
Conditioning	23°C, relative humidity 50% Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

	Length		Width	
	Front	Back	Front	Back
#1	*	*	*	*
#2	*	*	*	*
#3	*	*	*	*
#4	*	*	*	*
#5	*	*	*	*
#6	*	*	*	*
#7	*	*	*	*
#8	*	*	*	*
#9	*	*	*	*
#10	*	*	*	*

Flaming debris	no
Non-flaming debris	no

*: afterflame time ≤ 2 s
> 2 s: afterflame time > 2 s and ≤ 5 s
> 5 s: afterflame time > 5 s

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: T2407113_01d - Supreme F.R.

Classification of materials according to their reaction to fire - "Test for melting materials"

Date of ending the test	19-04-2024
Standard used	NF P92-505 (1995)
Product standard	NF P92-507 (2004)
Deviation from the standard	-
Dimension of the specimens	70 mm x 70 mm x 2 mm
Number of layers	2
Weight (g/m²)	286
Conditioning	23°C, relative humidity 50% Minimum 7 days or until constant mass is achieved

Four specimens, two on both sides, have been tested .

		First ignition (s)	Non-flaming debris	Flaming debris	Ignition cotton wool	Mass (g)
#1	front	*	yes	no	no	3.1
#2	back	*	yes	no	no	3.1
#3	front	*	yes	no	no	3.1
#4	back	*	yes	no	no	3.1

* no ignition

Classification M1